



Manufacturers and Distributors of Anti-Slip Treatments • Anti-Skid Coatings • Slip-Resistant Floor Care
• Anti-Slip FRP Panels & Step Covers • Safety Tapes • Anti-Slip Tapes

TECHNICAL DATA SHEET

SLIP RESISTANT WATER BASED EPOXY FLOOR COATING #79WB SERIES

DESCRIPTION

A one-part water reducible epoxy coating to give durable textured coating for foot traffic on steel, fiber glass, aluminum, concrete and wood substrates. For boat, trailer, laundry room, bathrooms, on steps, ramps and a variety of industrial and residential applications.

- Textured finish for slip resistance
- Single part epoxy – no mixing. Air dry
- Clear and white
- Lead and Chromate hazard free

PRODUCT CHARACTERISTICS

- A convenient and durable single part water based epoxy coating with integrated anti slip traction grit. Anti slip coating for concrete, primed wood, fiberglass, steel & treated aluminum.
- Application with roller. Touch dry in 30 to 40 minutes. Recoat time, 1 to 2 hours and full cure in 5-7 days at 25 Celsius or 77 Fahrenheit.
- Coverage of 300sq. ft. per gallon at 2 mils dry.
- Available in Grey 79WBG, White 79WBW, Clear 79WBC, Safety Yellow 79WBY

TECHNICAL DATA

Vehicle	Epoxy Ester
Volume Solids:	35% - 40% (dependant upon color)
Weight Solids:	45% - 50% (dependant upon color)
Weight/Gallon:	10 – 16 lb/gal (dependant upon color)
Viscosity:	90 -100 Krebs units
Gloss:	3 – 8 @ 60 reflectance
Coverage:	300sq. ft./gal @ 2 mil dry
Recommended Dry Film:	2.0 – 2.5 mils dry
Dry to Touch (@77°F):	30- 40 minutes
Recoat Time:	1 – 2 Hours
Full Cure:	5 – 7 days @ 77°F
Reducer:	Water
Max Reduction:	10% by volume

NOTICE: READ AND FULLY UNDERSTAND SDS BEFORE USING.

IMPORTANT NOTICE: This product is designed to help reduce the hazards of slippery areas when used with traction grit. This product cannot eliminate slipping. Seller and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for the intended purpose, and the user assumes all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer. Buyer assumes all risks and liability associated with disposal. E & OE

266 Wildcat Road, Toronto, ON Canada M3J 2N5

Phone: (416) 667-1788 Fax: (416) 667-1783 Toll Free: 1-800-375-0571 sales@noskidding.com www.noskidding.com